



KIPAS LINER (KTL) PAPER SPECIFICATION

TYPICAL CHARACTERISTICS

TEST	STANDART	BASIS WEIGHTS					
Basis weight g/m ²	ISO 536	110	120	135	140	150	175
Moisture %	ISO 287	8,5	8,5	8,5	8,5	8,5	8,5
SCT CD kN/m	ISO 9895	1,92	2,10	2,35	2,45	2,62	3,00
Burst kPa	ISO 2758	215	245	283	290	313	345
COBB60 g/m ²	ISO 535	30	30	30	30	30	30

GUARANTEED CHARACTERISTICS

TEST	STANDART	TOLERANCE	BASIS WEIGHTS					
Basis weight g/m ²	ISO 536	±5%	110	120	135	140	150	175
Moisture %	ISO 287	±3%	8,5	8,5	8,5	8,5	8,5	8,5
SCT CD kN/m	ISO 9895	Min.	1,60	1,75	1,97	2,03	2,18	2,45
Burst kPa	ISO 2758	Min.	209	228	257	266	285	315
COBB60 g/m ²	ISO 535	Max.	60	60	60	60	60	60

Testing atmosphere: % 50 ± 2, 23°C ± 1

Kipaş Kağıt Sanayi İşletmeleri A.Ş.
Adana Yolu Üzeri 21. Km Çakmak Mevkii
Kılılı / Turkoglu / Kahramanmaraş / Turkey
Phone Number +90 344 629 25 20
Fax +90 344 629 25 24
info@kipaskagit.com
www.kipaskagit.com/en

Date:02.05.2017
TS0015 Rev.04