



# MULTI-WHITE – White Testliner C

*A good compromise to balance out the economic and technical constraints*

CEPI CODE : 71

Revision 0 – 06/12/2018

## Nominal values

Characteristics	Units	Values							Toler	Norms
		120	125	130	135	140	160	175		
<b>Substance</b>	g/m <sup>2</sup>	120	125	130	135	140	160	175	+/-3%	ISO 536
<b>Bendtsen smoothness</b>	mL/mn	600	600	600	600	600	750	750	nominal	ISO 8791-2
<b>Burst</b>	kPa	215	225	235	245	255	290	300	nominal	ISO 2758
<b>SCT CD</b>	kN/m	1.55	1.65	1.70	1.75	1.80	1.95	2.10	nominal	ISO 9895
<b>Brightness Iso</b>	%	68	68	68	68	68	68	68	nominal	ISO 2470-1
<b>Cobb 1mn</b>	g/m <sup>2</sup>	25	25	25	25	25	25	25	Nominal	ISO 535
<b>Dennison</b>	N°	13	13	13	13	13	13	13	Nominal	TAPI T459
<b>Moisture content</b>	%	7,5	7,5	7,5	7,5	7,5	7,5	7,5	+/- 1	ISO 287

## Guaranteed values

Substance	g/m <sup>2</sup>	120	125	130	135	140	160	175	+/-3%	ISO 536
<b>Bendtsen smoothness</b>	mL/min	750	750	750	750	750	900	900	maxi	ISO 8791-2
<b>Burst</b>	kPa	190	200	210	215	225	240	265	mini	ISO 2758
<b>SCT CD</b>	kN/m	1.40	1.45	1.50	1.55	1.60	1.75	1.85	mini	ISO 9895
<b>Brightness Iso</b>	%	65	65	65	65	65	65	65	mini	ISO 2470-1
<b>Cobb 1mn</b>	g/m <sup>2</sup>	35	35	35	35	35	35	35	maxi	ISO 535
<b>Dennison</b>	N°	11	11	11	11	11	11	11	mini	TAPPI T459

Test carried out in laboratory conditions of 23°C and 50% relative humidity for 90% of the values

100% recycled

